


Organic Semiconducting Polymer Highly Regioregular P3HT




[P2513]

RR >99%

Advantages

- High regioregularity (RR) >99%
- Number average molecular weight: $M_n = 27,000 \sim 45,000$
- Electronic material grade: High purity, low metal (Pd <100 ppm)
- Highly soluble, excellent to film

Synthesis of P3HT by direct arylation polymerization (DAP) and physical properties^{1,2)}



The data is extracted from Ref. 2)

Method	M_n (PDI)	RR /%	T_m (°C)	μ_{max} (cm ² /V·s)
DAP	33,000 (1.8)	99.5	237	0.19
Rieke	25,000 (1.3)	95.5	224	0.02
GRIM	88,000 (1.5)	98.0	234	0.11

References 1) Q. Wang, R. Takita, Y. Kikuzaki, F. Ozawa, *J. Am. Chem. Soc.* **2010**, 132, 11420.
2) J.-R. Pouliot, M. Wakioka, F. Ozawa, Y. Li, M. Leclerc, *Macromol. Chem. Phys.* **2016**, 217, 1493.

Poly(3-hexylthiophene-2,5-diyl) (regioregular) [for organic electronics]


100mg / 500mg [P2513]

This product was commercialized by collaboration with Prof. Fumiuyuki Ozawa at Institute for Chemical Research, Kyoto University.

Organic Semiconducting Polymer: Highly Regioregular P3HT

Applications


Organic Photovoltaics (OPV)¹⁾



P3HT: Donor material

Usable for a solution processable OPV device
Fabricates a bulk heterojunction (BHJ) with a highly soluble donor and acceptor

Perovskite Solar Cell (PSC)²⁾



P3HT: Hole transport material (HTM)

Usable for a solution processable PSC device
Realizes high power conversion efficiency

Organic Transistor (OFET)³⁾



P3HT: p-Type semiconductor

Usable for a solution processable OFET device

References

- OPV:
 - E. L. Lim, C. C. Yap, M. A. M. Teridi, C. H. Teh, A. R. M. Yusof, M. H. H. Jumali, *Org. Electron.* **2016**, 36, 12.
 - A. Marrocchi, D. Lanari, A. Facchetti, L. Vaccaro, *Energy Environ. Sci.* **2012**, 5, 8457.
- PSC: L. Calió, S. Kazim, M. Grätzel, S. Ahmad, *Angew. Chem. Int. Ed.* **2016**, 55, 14522.
- OFET: H. Sirringhaus, *Adv. Mater.* **2014**, 26, 1319.

Ordering and Customer Service

TCI AMERICA

Tel : 800-423-8616 / 503-283-1681
Fax : 888-520-1075 / 503-283-1987
E-mail : Sales-US@TCIchemicals.com

TCI EUROPE N.V.

Tel : +32 (0)3 735 07 00
Fax : +32 (0)3 735 07 01
E-mail : Sales-EU@TCIchemicals.com

TCI Deutschland GmbH

Tel : +49 (0)6196 64053-00
Fax : +49 (0)6196 64053-01
E-mail : Sales-DE@TCIchemicals.com

Tokyo Chemical Industry UK Ltd.

Tel : +44 (0)1865 784560
Fax : +44 (0)1865 784561
E-mail : Sales-UK@TCIchemicals.com

TCI Chemicals (India) Pvt. Ltd.

Tel : 1800 425 7889 / 044-2262 0909
Fax : 044-2262 8902
E-mail : Sales-IN@TCIchemicals.com

梯希爱(上海)化成工业发展有限公司

Tel : 800-988-0390 / 021-67121386
Fax : 021-6712-1385
E-mail : Sales-CN@TCIchemicals.com

TOKYO CHEMICAL INDUSTRY CO., LTD.

Tel : +81 (0)3-5640-8878
Fax : +81 (0)3-5640-8902
E-mail : globalbusiness@TCIchemicals.com

Availability, price or specification of the listed products are subject to change without prior notice. Reproduction forbidden without the prior written consent of Tokyo Chemical Industry Co., Ltd.