


New

MATERIALS


TGI

# Acceptor-type Organic Semiconductor Building Blocks NTz and NOz


## Naphthobisthiadiazoles (NTz)



**NTz**  
[N1105]




**Br2-NTz**  
[D5288]




**Bpin2-NTz**  
[B5470]


## Naphthobisoxadiazoles (NOz)



**NOz**  
[N1137]



**Br2-NOz**  
[D5496]



**Bpin2-NOz**  
[B5774]

## Applications


### High-performance polymers for organic photovoltaics (OPV)

**PCE = 10.5%**

(ITO/ZnO/PNTz4TF2:PC<sub>71</sub>BM(1:2 w/w)/MoO<sub>x</sub>/Ag)

$\mu_{h,SCLC} = 1.5 \times 10^{-3} \text{ cm}^2/\text{Vs}$ ,  $\mu_{e,SCLC} = 2.1 \times 10^{-3} \text{ cm}^2/\text{Vs}$

1) K. Kawashima, T. Fukuhara, Y. Suda, Y. Suzuki, T. Koganezawa, H. Yoshida, H. Ohkita, I. Osaka, K. Takimiya, *J. Am. Chem. Soc.* **2016**, *138*, 10265.




**PNTz4TF2<sup>(1)</sup>**

**PCE = 10.3%**

(ITO/PEDOT:PSS/NT812:PC<sub>71</sub>BM(1:1.5 w/w)/PFN-Br/Ag)

$\mu_{h,SCLC} = 2.7 \times 10^{-2} \text{ cm}^2/\text{Vs}$


2) Y. Jin, Z. Chen, S. Dong, N. Zheng, L. Ying, X. F. Jiang, F. Liu, F. Huang, Y. Cao, *Adv. Mater.* **2016**, *28*, 9811.



**NT812<sup>(2)</sup>**

# Acceptor-type Organic Semiconductor Building Blocks NTz and NOz

## • Functional differences between benzothiadiazole and NTz analogs




	PCE (%)	$\mu_{hmax, SCLC}$ /cm <sup>2</sup> V <sup>-1</sup> s <sup>-1</sup>	$E_{HOMO}$ /eV	$E_{LUMO}$ /eV
<b>PBDT-DTNT</b>	<b>6.00</b>	<b>3.0×10<sup>-5</sup></b>	-5.19	-3.26
<b>PBDT-DTBT</b>	2.11	4.4×10 <sup>-6</sup>	-5.26	-3.10

3) M. Wang, X. Hu, P. Liu, W. Li, X. Gong, F. Huang, Y. Cao, *J. Am. Chem. Soc.* **2011**, *133*, 9638.

	PCE (%)	$\mu_{hmax, FET}$ /cm <sup>2</sup> V <sup>-1</sup> s <sup>-1</sup>	$E_{HOMO}$ /eV	$E_{LUMO}$ /eV
<b>PNTz4T</b>	<b>6.3</b>	<b>5.6×10<sup>-1</sup></b>	-5.16	-3.77
<b>PBTz4T</b>	2.6	7.4×10 <sup>-2</sup>	-5.07	-3.53

4) I. Osaka, M. Shimawaki, H. Mori, I. Doi, E. Miyazaki, T. Koganezawa, K. Takimiya, *J. Am. Chem. Soc.* **2012**, *134*, 3498.

## • Functional differences between NTz and NOz analogs



	PCE (%)	$E_{loss}$ /eV	$\mu_{h, FET}$ /cm <sup>2</sup> V <sup>-1</sup> s <sup>-1</sup>		$E_{HOMO}$ /eV	$E_{LUMO}$ /eV	
			on CF <sub>3</sub> (CF <sub>2</sub> ) <sub>7</sub> CH <sub>2</sub> CH <sub>2</sub> Si(OEt) <sub>3</sub> -treated substrates	on CH <sub>3</sub> (CH <sub>2</sub> ) <sub>17</sub> Si(OEt) <sub>3</sub> -treated substrates			
<b>PNOz4T</b>	8.9	0.52-0.56	5.5×10 <sup>-1</sup>	2.7×10 <sup>-1</sup>	1.7×10 <sup>-1</sup>	-5.48	-3.65
<b>PNTz4T</b>	10.1	0.82-0.85	2.3×10 <sup>-1</sup>	1.5×10 <sup>-1</sup>	-	-5.14	-3.46

5) K. Kawashima, I. Osaka, K. Takimiya, *Chem. Mater.* **2015**, *27*, 6558.

6) K. Kawashima, Y. Tamai, H. Ohkita, I. Osaka, K. Takimiya, *Nat. Commun.* **2015**, *6*, 10085.

- Naphtho[1,2-c:5,6-c']bis([1,2,5]thiadiazole) (=NTz)** 200mg [N1105]
- 5,10-Dibromonaphtho[1,2-c:5,6-c']bis([1,2,5]thiadiazole) (=Br2-NTz)** 100mg [D5288]
- Naphtho[1,2-c:5,6-c']bis([1,2,5]thiadiazole)-5,10-diboronic Acid Bis(pinacol) Ester (=Bpin2-NTz)** 100mg [B5470]
- Naphtho[1,2-c:5,6-c']bis([1,2,5]oxadiazole) (=NOz)** 200mg [N1137]
- 5,10-Dibromonaphtho[1,2-c:5,6-c']bis([1,2,5]oxadiazole) (=Br2-NOz)** 100mg [D5496]
- Naphtho[1,2-c:5,6-c']bis([1,2,5]oxadiazole)-5,10-diboronic Acid Bis(pinacol) Ester (=Bpin2-NOz)** 100mg [B5774]

These products were merchandized under the technical tie-up with Sankyo Kasei Co., Ltd.

## Related Products

- 2,1,3-Benzoxadiazole** 1g / 5g [B4473]
- 4,7-Dibromo-2,1,3-benzothiadiazol** 1g / 5g / 25g [D3842]
- 2,1,3-Benzothiadiazole-4,7-diboronic Acid Bis(pinacol) Ester** 1g / 5g [B3573]

For further information please refer to our website at [www.TCIchemicals.com](http://www.TCIchemicals.com).

Semiconductor



## Ordering and Customer Service

### TCI AMERICA

Tel : 800-423-8616 / 503-283-1681  
Fax : 888-520-1075 / 503-283-1987  
E-mail : Sales-US@TCIchemicals.com

### TCI EUROPE N.V.

Tel : +32 (0)3 735 07 00  
Fax : +32 (0)3 735 07 01  
E-mail : Sales-EU@TCIchemicals.com

### TCI Deutschland GmbH

Tel : +49 (0)6196 64053-00  
Fax : +49 (0)6196 64053-01  
E-mail : Sales-DE@TCIchemicals.com

### Tokyo Chemical Industry UK Ltd.

Tel : +44 (0)1865 784560  
Fax : +44 (0)1865 784561  
E-mail : Sales-UK@TCIchemicals.com

### TCI Chemicals (India) Pvt. Ltd.

Tel : 1800 425 7889 / 044-2262 0909  
Fax : 044-2262 8902  
E-mail : Sales-IN@TCIchemicals.com

### 梯希爱(上海)化成工业发展有限公司

Tel : 800-988-0390 / 021-67121386  
Fax : 021-6712-1385  
E-mail : Sales-CN@TCIchemicals.com

### TOKYO CHEMICAL INDUSTRY CO., LTD.

Tel : +81 (0)3-5640-8878  
Fax : +81 (0)3-5640-8902  
E-mail : globalbusiness@TCIchemicals.com

Availability, price or specification of the listed products are subject to change without prior notice. Reproduction forbidden without the prior written consent of Tokyo Chemical Industry Co., Ltd.